

# DALLAS LABORATORIES, INC.

Consultants and Technologists  
Chemical and Petroleum Chemists

P.O. BOX 152837, DALLAS, TEXAS 75315  
1323 WALL ST, DALLAS, TEXAS 75215  
PHONE 214/565-0593  
FAX 214/565-1094

MEMBERS  
AMERICAN CHEMICAL SOCIETY  
ASTM INTERNATIONAL  
AMERICAN SOCIETY OF MATERIALS

MEMBERS  
AMERICAN NATIONAL STANDARDS INSTITUTE  
AMERICAN SOCIETY FOR QUALITY CONTROL  
FEDERATION OF SOCIETIES FOR COATINGS TECHNOLOGY

Submitted by: SAPA Extrusions  
142 SAPA Drive  
Delhi, LA 71232

Date: August 12, 2014

Attn: Mike Copes

Report No: 46935

## REPORT

### Sample:

Anodized Finish, Class I, Bronze  
Coating: SAPA 215 Dark Bronze Anodize (lot #21687386)  
Pre-Treatment: Acid Etch / Caustic Etch  
Drawing: #TSW-276  
Production Date: 3/13/14

### A. PROCEDURE

Submitted sample was tested according to AAMA 611-12, "Voluntary Specification for Anodized Architectural Aluminum, Class I, Designation A44, all sections, except 8.7 Weather Exposure.

### B. RESULTS

<u>Test</u>	<u>Results</u>	<u>AAMA 611-12 (I) Specification Requirements</u>
8.1 Oxide Coating Thickness (mil) (ASTM B487)	0.70	0.70 min.
8.2 Oxide Coating Weight & Apparent Density (ASTM B137)	Pass	
8.2.1 Coating Weight (mg/in <sup>2</sup> )	27.0	27.0 min.
8.2.3 Apparent Density (g/in <sup>3</sup> )	38.6	38.0 min.
8.3 Color Uniformity ( $\Delta E$ ) (AATCC TM173)	1.2	5.0 max.
8.4 Gloss Uniformity (ASTM D523, 60°)	1.6	$\Delta$ 15.0 max.
8.5 Abrasion Resistance (Michael Clark Abrasion Test)	Pass	No bite or chalk dust pick-up

<u>Test</u>	<u>Results</u>	<u>AAMA 611-12 (I) Specification Requirements</u>
8.6 Corrosion Resistance (ASTM B117, 3000 hrs. using 5% salt solution)	Pass (No spots or pits)	No spots or pits larger than 1 mm
8.8 Seal Test (mg/in <sup>2</sup> ) (ASTM B680)	0.8	2.6 max loss
8.9 Craze Resistance, °F	Pass	No crazing @ 170° min

Date Testing Started: 3/31/14

Date Testing Completed: 8/12/14

Date Test Report Expires: 8/12/17

Sampled by: Initial Submittal

The test results indicate that the sample tested is in compliance with all of the performance requirements of AAMA 611-12 Class I except for Section 8.7 as procedurally noted.

**DALLAS LABORATORIES, INC.**



---

Kevan W. Jones, Vice President

Analyst: GF, TL  
KJ: js